



26.02.2013

PRE-TEX®
SUMMARY TABLES OF TEST RESULTS

| Test criteria | Pass or fail? |
|---------------------------------------|--|
| | “Pre-TEX Wash” |
| Health and Safety aspects | Final assessment was not possible, as the complete formulation was not disclosed. The product’s flashpoint fulfils the approval criterion. |
| Formulation stability | Pass |
| Iodine number | Pass |
| Solvent residue/VOC content | Pass |
| Swell test on printing blankets | Pass |
| Swell test on rollers | Pass |
| Compatibility test on printing plates | Borderline Pass Results for conventional positive plates and to some extent for ctp thermo positive plates were not clearly acceptable. |

| Test criteria | Pass or fail? |
|--------------------------------|--|
| | “Pre-TEX wash cloth” |
| Inspection of printing blanket | Pass |
| Solvent residue | Pass The amount of solvent residue was 49.2 pl/m ² |
| Abrasion resistance | Pass |
| Resistance to breaking | Pass 43,5N (lengthwise) /28,0 N (crosswise) |
| Resistance to deformation | Pass 26,7% (lengthwise) /68,5 (crosswise) |
| “Loose fibres” | Pass |